

ASLAN DFP 16

The translucent film for digital printing

The white, translucent digital print film with its semi-gloss surface is ideal for back-lit applications. It is suitable for electrostatic print (hot-transfer) thermotransfer printing and all printing methods with common solvent, eco-solvent inks, latex and UV-inks. A PE-coated release liner ensures an ideal print result due to its moisture stability and its optimized thermal conduction.

To protect your printing results from UV-radiation and other external influences and to extend the durability, we recommend the ASLAN-protective film.

ASLAN DFP 16 can be used for computerised cutting of designs and lettering etc.

For any further information please contact our technical advisory service:
+49 (0) 2204.708-80

CONSTRUCTION

| | | |
|-----------------------|---|--|
| face-film: | PVC (polymeric softeners) | |
| thickness: | ~ 90 µm | |
| adhesive: | acrylic pressure adhesive | square quantity: ~ 25 g/m ² |
| release liner: | PE-coated silicon cardboard (double sided) | square weight: ~ 144 g/m ² |

CHARACTERISTICS

| | | |
|---|--|-------------------------------------|
| adhesive strength: (ASTMD-903) | immediately after 1 week | ~ 6.3 N/25 mm ~ 10 N/25 mm |
| dimensional stability: | applied onto aluminium after 48 hours stored at 70 °C (25 x 25 cm) | max. -0.45 % |
| chemical resistance: | In a preece test of 24 hours the applied film is resistant to most petroleum based oils, greases and aliphatic solvents, mild acids, alkalies and salts. | |
| light proofness: | DIN 53 388 | non-fade grade: 6-8 (wool-scale) |
| light transmission: | DIN 53 147 | ~ 30% |

ASLAN DFP 16

CHARACTERISTICS

| | | |
|----------------------------|---|---------------------|
| combustibility: | stuck on aluminium, the film is self-extinguishing. | |
| temperature: | application temperature: | min. 15°C |
| | service temperature range: | -30 °C up to +80 °C |
| minimum durability: | 7 years outdoors, with vertical exposure, in middle-european climate. | |

PROCESSING

| | |
|----------------------|---|
| printability: | The material is printable with solvent, eco-solvent, UV-curable and latex inks. (In case of inadequate drying of the print-inks the film will be sodded and the adhesive negatively affected.) |
| application: | Application dry or damp. If applicated damp, a possible whiteing of the adhesive occurs but will fade away after a couple of days depending on the weather. For a damp application we recommend the transferliquide ASLAN TL10. For the application of letterings etc. we recommend our ASLAN Application Tapes respectively the ASLAN TMO. |
| storage life: | Before application the films can be stored for minimum 3 years from date of production. The film must be stored at room temperature (15-25 °C) and a relativ humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed `hanging´ racks. |

state: 04/2010

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test our products suitability for the purpose intended.

The quality of our products is regularly examined, upgraded and developed. We reserve the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of their products in accordance with their latest knowledge.

ASLAN, Schwarz GmbH & Co. KG

POB 5165 · D-51486 Overath · Oberauel 2 · D-51491 Overath · Germany

fon +49 (0) 2204.708-80 · fax +49 (0) 2204.708-50 · e-mail info@ASLAN-schwarz.com

www.ASLAN-schwarz.com