

ASLAN EL 210



The translucent glass-decoration film with frosted glass-effect for long-term applications

The white translucent self-adhesive film with milk glass effect and medium translucency offers manifold options for decoration of glass.

Its reduced surface gloss avoids unwanted reflections and is ideal for all decorations on glass.

ASLAN EL 210 is ideal for computerised cutting of letterings, logos etc.

The ASLAN Dryapply technology has been designed especially for the dry application on large surfaces and guarantees an easy application even for inexperienced users, because bubbles can be easily wiped out.

The textured liner creates air channels in the adhesive and makes the application easy and efficient. The honeycomb pattern vanishes shortly after application on glass.

The width of 1.37 m is ideal for most printing needs.

For any further information please contact our technical advisory service:
+49 (0)2204.708-80

CONSTRUCTION

face-film:	PVC (polymeric softened)	
thickness:	~ 80 µm	
adhesive:	acrylic pressure adhesive	square quantity: ~ 25 g/m ²
release liner:	silicone cardboard PE-coated on both sides	square weight: ~ 144 g/m ²

CHARACTERISTICS

adhesive strength: (ASTMD-903)	immediately after 1 week	~ 2,5 N/25 mm ~ 10 N/25 mm
dimensional stability:	applied onto aluminium after 48 hours stored at 70 °C (25 x 25 cm)	max. -0.45 %
chemical resistance:	In a prece test of 24 hours the applied film is resistant to most petroleum based oils, greases and aliphatic solvents, mild acids, alkalis and salts.	
light proofness:	DIN 53 388	non-fade grade: 7-8 (Woll-Scale)
light transmission:	DIN 53 147	~ 97% (E 200), ~46% (E 210), ~ 66.5% (E 300)
combustibility:	stuck on aluminium, the film is self-extinguishing.	

ASLAN EL 210



CHARACTERISTICS

temperature:	application temperature: min. 15°C service temperature range: -30 °C up to +80 °C
minimum durability:	7 years outdoors, with vertical exposure, in middle-european climate.

PROCESSING

application:	Dry application only For the application of letterings etc. we recommend our ASLAN application tapes respectively the ASLAN TMO.
storage life:	Before application the films can be stored for minimum 3 years from date of production. The film must be stored at room temperature (15-25 °C) and a relativ humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed `hanging´ racks.

state: 11|2011

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test our products suitability for the purpose intended.

The quality of our products is regularly examined, upgraded and developed. We reserve the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of their products in accordance with their latest knowledge.

ASLAN, Schwarz GmbH & Co. KG

POB 5165 · D-51486 Overath · Oberauel 2 · D-51491 Overath · Germany
fon +49 (0) 2204. 708-80 · **fax** +49 (0) 2204. 708-50 · **e-mail** info@ASLAN-schwarz.com

www.ASLAN-schwarz.com